



PRODUCT DATA SHEET

Sikaflex®-268

Assembly & glazing adhesive and sealant for rail applications with acceleration option

TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Chemical base	1-component polyurethane
Colour (CQP001-1)	Black
Cure mechanism	Moisture-curing
Density (uncured)	1.3 kg/L
Non-sag properties (CQP061-1)	Very good
Application temperature	5 °C – 40 °C
Skin time (CQP019-1)	60 minutes ^A
Open time (CQP526-1)	40 minutes ^A
Curing speed (CQP049-1)	(see diagram)
Shrinkage (CQP014-1)	1 %
Shore A hardness (CQP023-1 / ISO 48-4)	55
Tensile strength (CQP036-1 / ISO 527)	6 MPa
Elongation at break (CQP036-1 / ISO 527)	500 %
Tear propagation resistance (CQP045-1 / ISO 34)	13 N/mm
Tensile lap-shear strength (CQP046-1 / ISO 4587)	4.5 MPa
Service Temperature (CQP509-1 / CQP513-1)	-50 °C – 90 °C
Shelf life (CQP016-1)	unipack 12 months ^B
	pail 6 months ^B

CQP = Corporate Quality Procedure

^{A)} 23 °C / 50 % r. h.

^{B)} storage below 25 °C)

DESCRIPTION

Sikaflex®-268 is an adhesive system specifically designed for the rail industry. It is suitable for assembly bonding and glazing applications; its outstanding weathering resistivity and unique resistance to a wide variety of cleaning agents make it an ideal solution for use in exterior joints in the rail industry.

Sikaflex®-268 is compatible with Sika's black-primerless bonding process.

Sikaflex®-268 can be accelerated with Sika's Booster and PowerCure systems.

PRODUCT BENEFITS

- Resistant to a wide variety of cleaning agents
- Passes EN45545 R1/R7 HL3
- Curing can be accelerated with Sika® Booster and Sika® PowerCure
- Excellent weathering stability
- Very good processing and tooling characteristics
- Solvent-free

AREAS OF APPLICATION

Sikaflex®-268 is designed for assembly and direct-glazing applications in rail, the commercial vehicle industry and for the repair market.

It exhibits excellent tooling and application properties. With its superior resistance to a wide range of cleaning agents combined with outstanding weathering resistance, it can be used for exterior joints.

Seek manufacturer's advice and perform tests on original substrates before using Sikaflex®-268 on materials prone to stress cracking.

Sikaflex®-268 is suitable for experienced professional users only. Test with actual substrates and conditions have to be performed ensuring adhesion and material compatibility.

PRODUCT DATA SHEET

Sikaflex®-268

Version 04.01 (04 - 2022), en_CA

012001212680001000

CURE MECHANISM

Sikaflex®-268 cures by reaction with atmospheric moisture. At low temperatures the water content of the air is generally lower and the curing reaction proceeds somewhat slower (see diagram 1).

Diagram 1: Curing speed Sikaflex®-268

CHEMICAL RESISTANCE

Sikaflex®-268 is generally resistant to fresh water, seawater, diluted acids and diluted caustic solutions; temporarily resistant to fuels, mineral oils, vegetable and animal fats and oils; not resistant to organic acids, glycolic alcohol, concentrated mineral acids and caustic solutions or solvents.

It is resistant to a wide range of rail cleaning agents if used according to the guidelines of the manufacturer. Some rail cleaning agents contain aggressive chemicals such as phosphoric acids which may influence the durability of Sikaflex®-268 significantly. Therefore it is of highest importance to limit the exposure time to a minimum, observe correct dilution of cleaning agent and to perform a thorough rinsing after the cleaning process. Test newly introduced cleaning agents.

The above information is offered for general guidance only. Advice on specific applications will be given on request.

METHOD OF APPLICATION

Surface Preparation

Surfaces must be clean, dry and free from grease, oil and dust. Surface treatment depends on the specific nature of the substrates and is crucial for a long lasting bond. All pre-treatment steps must be confirmed by preliminary tests on original substrates considering specific conditions in the assembly process.

Application

Sikaflex®-268 can be applied at temperatures ranging between 5 °C and 40 °C (climate and product) but changes in reactivity and application properties have to be taken into consideration. The optimum temperature for substrate and sealant is between 15 °C and 25 °C.

Consider the viscosity increase at low temperature. For easy application, condition the adhesive at ambient temperature prior to use. To ensure a uniform thickness of the bondline it is recommended to apply the adhesive in form of a triangular bead (see figure 1).




Figure 1: Recommended bead configuration

Sikaflex®-268 can be applied with hand, pneumatic or electric driven piston guns as well as pump equipment. The open time is significantly shorter in hot and humid climate. The parts must always be installed within the open time. Never join bonding parts if the adhesive has built a skin.

For advice on selecting and setting up a suitable pump system, contact Sika Canada.

Tooling and finishing

Tooling and finishing must be carried out within the open time of the adhesive. We recommend the use of Sika® Tooling Agent N. Other finishing agents must be tested for suitability and compatibility.

Removal

Uncured Sikaflex®-268 can be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once cured, the material can only be removed mechanically.

FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheets
- General Guidelines
Bonding and Sealing with 1-component Sikaflex®

PACKAGING INFORMATION

Unipack	600 mL
Pail	23 L

BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

HEALTH AND SAFETY INFORMATION

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

DISCLAIMER

The information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The information contained herein does not relieve the user of the products from testing them for the intended application and purpose. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request or may be downloaded from our website at: www.sika.ca

PRODUCT DATA SHEET

Sikaflex®-268
Version 04.01 (04 - 2022), en_CA
012001212680001000

Sika Canada Inc.
Head Office
601, avenue Delmar
Pointe-Claire, Quebec
H9R 4A9
1-800-933-SIKA
www.sika.ca

