

PRODUCT DATA SHEET

# Sikaflex®-554

STP assembly bonding adhesive with acceleration option

**TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)**

Chemical base		Silane Terminated Polymer
Colour (CQP001-1)		White, black
Cure mechanism		Moisture-curing
Density (uncured)	depending on color	1.44 kg/l
Non-sag properties		Good
Application temperature	ambient	5 °C – 40 °C
Skin time (CQP019-1)		25 minutes <sup>A</sup>
Open time (CQP526-1)		20 minutes <sup>A</sup>
Curing speed (CQP049-1)		see diagram 1
Shrinkage (CQP014-1)		2 %
Shore A hardness (CQP023-1 / ISO 48-4)		55
Tensile strength (CQP036-1 / ISO 527)		3.5 MPa
Elongation at break (CQP036-1 / ISO 527)		500 %
Tear propagation resistance (CQP045-1 / ISO 34)		20 N/mm
Tensile lap-shear strength (CQP046-1 / ISO 4587)		2.5 MPa
Service Temperature (CQP509-1 / CQP513-1)		-50 °C – 90 °C
Shelf life (CQP016-1)	unipack / cartridge drum / pail	12 months <sup>B</sup> 9 months <sup>B</sup>

CQP = Corporate Quality Procedure

<sup>A)</sup> +23 °C / 50 % r. h.

<sup>B)</sup> Stored below +25 °C

**DESCRIPTION**

Sikaflex®-554 is an elastic 1-component Silane Terminated Polymer (STP) adhesive system especially designed for bonding large components in industrial assembly. It bonds well to a wide range of substrates with minimal pre-treatment.

Sikaflex®-554 can be accelerated with Sika's Booster and PowerCure systems.

**PRODUCT BENEFITS**

- Good adhesion to a wide variety of substrates without primer
- Very good weathering resistance
- Passes DIN EN 45545-2 R1/R7 HL3
- ISEGA certificate for foodstuff area usage
- Curing can be accelerated with Sika Booster and Sika PowerCure
- Solvent-, isocyanate-, phthalate- and PVC-free
- Capable of withstanding dynamic stresses

**AREAS OF APPLICATION**

Sikaflex®-554 is suitable for joints that will be subjected to dynamic stresses. Suitable substrate materials: metals, aluminum, metal primers, paint coatings, sheet steel, ceramic materials and certain plastics. It bonds well to a wide range of substrates with minimal pre-treatment. Seek manufacturer's advice and perform tests on original substrates before using Sikaflex®-554 on materials prone to stress cracking. Sikaflex®-554 is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed ensuring adhesion and material compatibility.

**PRODUCT DATA SHEET**

Sikaflex®-554

Version 03.01 (04 - 2022), en\_CA  
012201215540001010

## CURE MECHANISM

Sikaflex®-554 cures by reaction with atmospheric moisture. At low temperatures the water content of the air is generally lower and the curing reaction proceeds somewhat slower (see diagram 1).




Diagram 1: Curing speed Sikaflex®-554

## CHEMICAL RESISTANCE

Sikaflex®-554 is generally resistant to fresh water, seawater, diluted acids and diluted caustic solutions; temporarily resistant to fuels, mineral oils, vegetable and animal fats and oils; not resistant to organic acids, glycolic alcohol, concentrated mineral acids and caustic solutions or solvents.

## METHOD OF APPLICATION

### Surface Preparation

Surfaces must be clean, dry and free from grease, oil, dust and contaminants.

Surface treatment depends on the specific nature of the substrates and is crucial for a long lasting bond. Suggestions for surface preparation may be found on the current edition of the appropriate Sika® Pre-treatment Chart. Consider that these suggestions are based on experience and have in any case to be verified by tests on original substrates.

### Application

Sikaflex®-554 can be processed between +5 °C and +40 °C (climate and product) but changes in reactivity and application properties have to be considered. The optimum temperature for substrate and sealant is between +15 °C and +25 °C. Consider that viscosity will increase at low temperature. For easy application, condition the adhesive at ambient temperature prior to use. To ensure a uniform thickness of the bondline it is recommended to apply the adhesive in form of a triangular bead (see figure 1).




Figure 1: Recommended bead configuration

Sikaflex®-554 can be processed with manual, pneumatic or electric driven piston guns as well as pump equipment. The open time is significantly shorter in hot and humid climate. The parts must always be installed within the open time. Never join bonding parts if the adhesive has built a skin. For advice on selecting and setting up a suitable pump system, contact Sika Canada.

### Tooling and finishing

Tooling and finishing must be carried out within the skin time of the product. It is recommended using Sika® Tooling Agent N. Other finishing agents must be tested for suitability and compatibility prior the use.

### Removal

Uncured Sikaflex®-554 may be removed from tools and equipment with Sika® Remover-208 or another suitable solvent. Once cured, the material can only be removed mechanically. Hands and exposed skin have to be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water.

## FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from Sika Canada. Copies of the following publications are available on request:

- Safety Data Sheets
- Sika Pre-treatment Chart
  - For Silane Terminated Polymers (STP)
- General Guideline
  - Bonding and Sealing with 1-component Sikaflex®

## PACKAGING INFORMATION

Unipack	600 mL
Cartridge	300 mL
Pail	23 L
Drum	195 L

## BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## HEALTH AND SAFETY INFORMATION

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

## DISCLAIMER

The information, and in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any recommendations, or from any other advice offered. The information contained herein does not relieve the user of the products from testing them for the intended application and purpose. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request or may be downloaded from our website at: [www.sika.ca](http://www.sika.ca)

## PRODUCT DATA SHEET

Sikaflex®-554  
Version 03.01 (04 - 2022), en\_CA  
012201215540001010

Sika Canada Inc.  
Head Office  
601, avenue Delmar  
Pointe-Claire, Quebec  
H9R 4A9  
1-800-933-SIKA  
[www.sika.ca](http://www.sika.ca)

