

# PRODUCT DATA SHEET

## SikaCor® EG-5

### 2-PACK AY-PUR TOP COAT

#### DESCRIPTION

SikaCor® EG-5 is a 2-pack acrylic polyurethane top coat.  
Suitable for use in hot and tropical climatic conditions.

#### USES

SikaCor® EG-5 may only be used by experienced professionals.

In combination with 2-pack primer and intermediate coats of the SikaCor® and Sika® Permacor® product range for heavy duty corrosion protection of steel structures.

Also suitable for submerged steel.

#### CHARACTERISTICS / ADVANTAGES

Combined with 2-pack epoxy primer and intermediate coats:

- Very good corrosion protection properties
- Excellent chemical, weather and colour stability
- Tough elastic and hard but not brittle
- Largely insensitive against shock and impact

#### APPROVALS / CERTIFICATES

- Approved according to German standard 'TL/TP-KOR-Stahlbauten', page 87 and page 94.
- In combination with SikaCor® PUR Accelerator, SikaCor® EG-5 is approved according to German standard 'TL/TP-KOR-Stahlbauten', page 97.

#### PRODUCT INFORMATION

Packaging	SikaCor® EG-5	30 kg and 10 kg net.
Appearance / Colour	RAL and NCS colour shades	
Shelf life	2 years from date of manufacture	
Storage conditions	In originally sealed containers in a cool and dry environment.	
Density	~1.3 kg/l	
Solid content	~61 % by volume ~74 % by weight	

## TECHNICAL INFORMATION

<b>Chemical Resistance</b>	Weather, water, sewage, seawater, smoke, de-icing salts, acid and lye vapours, oils, grease and short term exposure to fuels and solvents.
<b>Temperature Resistance</b>	Dry heat up to +150 °C, short term up to +180 °C Damp heat up to approximately +50 °C In case of higher temperatures please consult Sika.

## SYSTEMS

<b>Systems</b>	<u>Steel:</u> Used as top coat on 2-pack primer and intermediate coats of the SikaCor® and Sika® Permacor® product range.  <u>Galvanized steel, stainless steel and aluminium:</u> 1 x SikaCor® EG-1 or SikaCor® EG-1 VHS 1 x SikaCor® EG-5  In case of light colours a second top coat of SikaCor® EG-5 may become necessary to achieve perfect opacity.
----------------	--

## APPLICATION INFORMATION

<b>Mixing Ratio</b>	Components A : B	
	By weight	90 : 10
	By volume	7.1 : 1
<b>Thinner</b>	Sika® Thinner EG If necessary maximum 5 % Sika® Thinner EG may be added to adapt the viscosity.	
<b>Consumption</b>	Theoretical material-consumption/VOC without loss for medium dry film thickness:	
	Dry film thickness	60 µm                      80 µm
	Wet film thickness	100 µm                      130 µm
	Consumption	~0.130 kg/m <sup>2</sup> ~0.170 kg/m <sup>2</sup>
	VOC	~33.2 g/m <sup>2</sup> ~44.3 g/m <sup>2</sup>
<b>Product Temperature</b>	+5 °C min. / +35 °C max.	
<b>Relative Air Humidity</b>	Maximum 85 %, except the surface temperature is significantly higher than the dew point temperature, it shall be at least 3 °C above dew point. The surface must be dry and free from ice.	
<b>Surface Temperature</b>	Minimum +5 °C 0 °C by adding SikaCor® PUR Accelerator	
<b>Pot Life</b>	+10 °C	~7 h                      ~5 h *
	+20 °C	~5 h                      ~3 h *
	+30 °C	~4 h                      ~2 h *
	(*Adding 1 % by weight SikaCor® PUR Accelerator)	
<b>Drying Stage 6</b>	<b>Dry film thickness 80 µm</b>	(ISO 9117-5)
	+5 °C	21 h
	+10 °C	18 h
	+20 °C	14 h
	+40 °C	3 h
	+80 °C	45 min

Adding 1 % by weight SikaCor® PUR Accelerator

	Dry film thickness 80 µm
0 °C	52 h
+5 °C	18 h
+10 °C	13 h
+20 °C	5 h

(ISO 9117-5)

**Waiting Time / Overcoating** Minimum waiting time until drying stage 6 is achieved to unlimited maximum time.

Prior to further applications possible contamination must be removed (see page 3 surface preparation).

**Drying time** **Final drying time**  
Depending on film thickness and temperature full hardness is achieved after 1 to 2 weeks. Tests of the completed coating system should only be carried out after final curing.

## APPLICATION INSTRUCTIONS

### SURFACE PREPARATION

#### Steel:

Blast cleaning to Sa 2 ½ according to ISO 12944, part 4. Free from dirt, oil and grease.

#### Galvanized steel, stainless steel and aluminium:

Free from dirt, oil, grease and corrosion products. In case of permanent immersion and condensation the surfaces must be slightly sweep blasted with non-ferrous abrasives.

Contaminated surfaces for example galvanized or primed areas we recommend to clean with SikaCor® Wash.

### MIXING

Stir component A very thoroughly using an electric mixer (start slowly, then increase up to approximately 300 rpm). Add component B carefully and mix both components very thoroughly (including sides and bottom of the container). Mix for at least 3 minutes until a homogeneous mixture is achieved. Fill mixed material into clean container and mix again shortly as described above.

### APPLICATION

The method of application has a major effect on achieving uniform thickness and appearance. Spray application will give the best results. The indicated dry film thickness is easily achieved by airless spray. Adding solvents reduces the sag resistance and the dry film thickness. In case of application by roller or brush, additional applications may become necessary to achieve the required coating thickness, depending on type of construction, site conditions, colour shade etc. Prior to major coating operations a test application on site may be useful to ensure the selected application method will provide the requested results.

#### By brush and roller

#### Conventional high pressure spraying:

- Nozzle size 1.5 - 2.5 mm
- Pressure 3 - 5 bar
- Oil and water trap is compulsory

#### Airless-spraying:

- Pressure minimum 180 bar
- Nozzle size 0.38 - 0.53 mm (0.015 - 0.021 inch)
- Spraying angle 40° - 80°

### CLEANING OF EQUIPMENT

SikaCor® Cleaner

Spraying equipment must be rinsed with Sika® Thinner EG before using SikaCor® EG-5.

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### SIKA NORTHERN GULF

Bahrain / Qatar / Kuwait  
Tel: +973 177 38188  
sika.gulf@bh.sika.com  
gcc.sika.com

### SIKA SOUTHERN GULF

UAE / Oman / SIC  
Tel: +971 4 439 8200  
info@ae.sika.com  
gcc.sika.com

### SIKA SAUDI ARABIA

Riyadh / Jeddah / Damman  
Tel: +966 11 217 6532  
info@sa.sika.com  
gcc.sika.com



ISO 9001: Sika UAE LLC,  
Sika Gulf B.S.C. (c),  
Sika Saudi Arabia Co. Ltd,  
Sika Qatar LLC  
ISO 14001: Sika UAE LLC,  
Sika Gulf B.S.C. (c),  
Sika Saudi Arabia Co. Ltd  
OHSAS: Sika UAE LLC,  
Sika Gulf B.S.C. (c)

All products are supplied  
under a management  
system certified to conform  
to the requirements of the  
quality, environmental and  
occupational health &  
safety standards ISO 9001,  
ISO 14001 and OHSAS  
18001.

### Product Data Sheet

SikaCor® EG-5

October 2016, Version 02.03  
020602000040000004

SikaCorEG-5-en-AE-(10-2016)-2-3.pdf

